ProRox® MA 950 ALU



ProRox MA 950 ALU is a durable stone wool insulation blanket that is coated on one side with reinforced aluminum foil.

Application

The blanket is suitable for insulating industrial applications, such as tanks, columns, and constructions with irregular shapes.

Product properties in accordance with EN 14303

CE

Properties	Performance									Norms
Thermal conductivity at mean temperature	T (°C)	50	100	200	300	400	500	600	650	EN 12667
	λ (W/mK)	0,040	0,046	0,063	0,087	0,117	0,155	0,201	0,228	
Maximum service temperature	650°C The outer surface temperature for ALU faced products should be limited to 80°C									EN 14706
Reaction to fire	Euroclass A1L-S1,d0									EN 13501-1
Nominal density	≥ 80 kg/m3									EN 1602
Water absorption	≤ 1 kg/m2									EN 1609 EN ISO 29767
EN 14303 Designation code	MW EN 14303-T4-ST(+)650-WS1									EN 14303

Compliance

- ProRox MA 950 ALU insulation mats comply fully with EN 14303 requirements.
- ROCKWOOL stone wool insulation is made from volcanic rock and is not classified as a hazardous substance in accordance with Note Q, regulation (EC) No. 1272/2008.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL A/S and cannot be used without a prior written consent.