

ProRox® SL 978

ProRox SL 978 is a strong and rigid stone wool slab, for the thermal and acoustic insulation of constructions where higher temperatures and light mechanical loads (e.g. vibrations) occur. Typical examples are ovens, furnaces and exhaust ducts.



Product properties in accordance with IS 8183

Properties ¹	Performance							Standard
Thermal conductivity ² at mean temperature	T _m (°C) λ (W/mK)	50 0.041	100 0.049	150 0.057	200 0.065	250 0.075	300 0.086	IS 3346
Nominal density	128 kg/m ³							IS 3144
Max service temperature	650°C							ASTM C411 / C447
Heat resistance	No visible deterioration of fibrous structure. No evidence of self heating. No fusion of fibres at 750 °C							IS 3144
Incombustibility	< 5 wt%							IS 3144
Reaction to fire	EuroClass A1 Surface burning characteristic; Flame spread = Passed, Smoke development = Passed							EN 13501-1 ASTM E84
pH	7-10							IS 3144
Sulphur content	< 0.3 vol%							IS 3144
Chloride content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795							IS 3144 ASTM C692 / C871
Moisture absorption	Less than 1 wt%							IS 3144
Shot content	>250µm < 8 wt% >500µm < 3 wt%							IS 3144

1. All information and data for technical parameters in this data sheet are based on laboratory testing

2. Nominal values.

Compliance

- ProRox SL 978 slabs fully comply with the requirements as set by IS 8183 and other internationally recognized standards.
- Above product properties reflect only to IS standards. Compliance and Performance according to ASTM can be found on our website. Please contact our sales representatives for an extended list of approvals & certifications.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.



ROXUL ROCKWOOL Technical Insulation India Private Limited
Wing B-2, 2nd Floor, Unit No. 205,
Boomerang, Near Chandivali Film
Studio, Chandivali Farm Road,
Andheri (E), Mumbai – 400 072,
Maharashtra, India
T (+91) 022 6715 7700
F (+91) 022 6715 7710

**ROXUL-ROCKWOOL
Insulation India Private Limited**
Plot - Z/4, Dahej SEZ, Dahej,
District Bharuch – 392 130,
Gujarat, India
T (+91) 2641 264400

Toll Free 18002669861

ROCKWOOL Technical Insulation
www.rockwoolasia.com

PRODUCT DATA SHEET
200 336IN-07/20_V3 (EN)
PROROX INDUSTRIAL INSULATION